

Containing an insignificant amount of oxygen compared to ETP copper, C102 offers the highest purity copper available commercially. C102 or Oxygen-Free copper is ideal for applications where extremely high electrical conductivity and resistance to hydrogen embrittlement are vital. Where glass-to-metal seals are required this material also provides the added advantage of developing an adherent, non-scaling oxide at elevated temperatures. For more information contact Olin Brass Market Development Engineering at 618-258-5255, OlinBrass.com or email us at info@olinbrass.com.

Chemical Composition

Copper ¹	99.95% Min
Oxygen	0.001% Max

¹ Copper values includes Ag.




Figure 1: Comparison of Yield Strength and Electrical Conductivity performance of select Hard temper copper based materials.

Physical Properties

	English Units	Metric Units
Density	0.323 lb/in ³ @ 68°F	8.94 g/cm ³
Thermal Conductivity	226 BTU-ft/ft ² -hr-°F	390 W/mK
Electrical Resistivity	10.3 ohm circ mils/ft	1.71 microhm-cm
Electrical Conductivity (annealed)	101 % IACS*	0.586 megamho/cm
Modulus of Elasticity	17,000,000 psi	117 kN/mm ²
Coeff. Of Thermal Expansion	9.8 PPM/°F	17.64 PPM/°C

*International Annealed Copper Standard

Mechanical Properties

Temper ¹	Tensile Strength		Yield Strength		% Elongation ²	Typical 90° Bend Formability	
	ksi	N/mm ²	ksi	N/mm ²		GW/BW ³	
Annealed (Soft) ⁴	26-38	180-260	10	70	35	-	-
1/4 Hard	34-42	235-290	32	220	23	-	0.3
1/2 Hard	37-46	255-315	37	255	20	-	0.5
3/4 Hard	41-50	285-345	43	295	14	0.3	0.8
Hard	43-52	295-360	45	310	9	0.8	1.0
Extra Hard	47-56	325-385	50	345	4	1.3	1.5
Spring	50-58	345-400	52	360	3	1.8	2.0
Extra Spring	52 min	360 min	51 min	350 min	3 max		

¹ Mechanical properties subject to change. All rolled- tempers are accepted or rejected based on Tensile Strength.

² Nominal Values in 2" (51mm)

³ DATA FOR REFERENCE ONLY. R/T = Bend Radius/Material Thickness <0.016" (0.4mm) thick, 11/16 (17.5mm) wide.

⁴ Annealed temper are manufactured to a grain size only, consult mill for additional info.

Olin Brass Headquarters

4801 Olympia Park
Plaza, Suite 3500
Louisville, KY 40241
Ph: 502-873-3000

GBC METALS ASIA PACIFIC PTE LTD

1 Kim Seng Promenade
Great World City, E Tower
Singapore 237994
Ph: 65.6238.1155

GBC METALS LLC SHANGHAI

Room 2004 Aetna Tower
No. 107 Zunyi Rd
Shanghai 200051 China
Ph: 86.21.6237.5898

OLIN BRASS-HEADQUARTERS

4801 Olympia Park
Plaza, Suite 3500
Louisville, KY 40241
Ph: 502-873-3000

OLIN BRASS - MILL

285 Lewis & Clark Blvd.
East Alton, IL 62024
Ph: 618-258-5255

BRYAN METALS INC.

1103 South Main Street
Bryan OH 43506-0487
Ph: 419-636-4571
Fx: 419-636-3994

SOMERS THIN STRIP

215 Piedmont Street
Waterbury, CT 06706
Ph: 203-597-5000
Fx: 203-597-5081

A.J. OSTER COMPANY

180 ALEXANDRA WAY
Carol Stream, IL 60188-2068
Ph: 630-260-1040
Ph: 800-323-9644
Fx: 630-260-1102

A.J. OSTER CARIBE, INC.

Centro industrial Rio Canas
Lote 29, P.M.B HC-01
Box 29030
Caguas, PR 00725
Ph: 787-747-7575

A.J. OSTER FOILS, INC.

2081 McCrea Street
Alliance, OH 44601-2793
Ph: 330-823-1700
Ph: 800-321-9750
Fx: 330-823-1705

A.J. OSTER WEST INC.

22833 La Palma Avenue
Yorba Linda, CA 92887-4767
Ph: 714-692-1000
Ph: 800-933-5933
Fx: 714-692-1225

A.J. OSTER COMPANY

457 Industrial Drive
Warwick, RI 02886
Ph: 401-739-0800
Fx: 401-739-1276

INTERNATIONAL SALES OFFICES & FACILITIES**GBC METALS ASIA PACIFIC PTE LTD.**

1 Kim Seng Road Promenade
Great World City, East Tower #13-04
Singapore 237994
Ph: 65.6238.1155
Fx: 65.6238.0660

GBC METALS LLC SHANGHAI

Room 2004, Aetna Tower
No. 107 Zunyi Road
Shanghai 200051, China
Ph: 86.21.6237.5898
Fx: 86.21.6237.5805

OLIN LUOTONG METALS (GZ) Co Ltd

No. 8 Jung Gong Road, East District
Guangzhou Economic Technological & Dev District
Guangzhou, P.R. China 510530
Ph: 86.20.8226.6818
Fx: 86.20.8226.6718

DOWA-OLIN METAL CORPORATION

2630, Shingai
Iwata-shi, Shiznoka-ken
438, Japan
Ph: 81.538.37.5111
Fx: 81.538.37.0147

OLIN BRASS - INTERNATIONAL DISTRIBUTORS**UNITED KINGDOM / IRELAND****Aurubis UK Ltd.**

Rabone Park, Smethwick
West Midlands B66 2NN
England
Ph: 44 (0) 121 555 1199
Fx: 44 (0) 121 555 1188
Email: info-uk@aurubis.com
Website: www.aurubis.com

EUROPE**Walter Türkis GmbH**

Struthstrasse 35
55743 Idar-Oberstein
Germany
Ph: 49 (0) 6781 62-0
Fx: 49 (0) 6781 62-28
Email: service@tuerkis-schneid-center.de
Website: www.tuerkis-schneid-center.de

OLIN BRASS MEXICO S.A. de CV

Av. La Griega # 117
Parque Industrial Queretaro
Santa Rosa, Jaurgui
Queretaro, Mexico 76220
Ph: 52 442 2 29 40 00
Fx: 52 442 2 29 40 29